

Agilus30



PolyJet Rubberlike Material

Agilus30™ is a superior rubberlike PolyJet™ photopolymer family ideal for advanced design verification and rapid prototyping. Get more durable, tear-resistant prototypes that can stand up to repeated flexing and bending. With a Shore A value of 30 in clear, black and white, Agilus30 accurately simulates the look, feel and function of rubber-like products. 3D print rubber surrounds, overmolds, soft-touch coatings, living hinges, jigs and fixtures, wearables, grips and seals with improved surface texture.

Mechanical Properties	Test Method	Value	
		Black / Translucent	White
Tensile Strength	ASTM D-412	2.4 – 3.1 MPa (348 – 450 psi)	2.1-2.6 MPa (305 – 377 psi)
Elongation at Break	ASTM D-412	220 – 270%	185 – 230%
Compressive Set	ASTM D-395	6 – 7%	6 – 7%
Tensile Tear Resistance	ASTM D-624	4 – 7 Kg/cm (22 – 39 lb/in)	4 – 7 Kg/cm (22 – 39 lb/in)

Other	Test Method	Value	
		Black / Translucent	White
Shore Hardness	ASTM D-2240	30 – 35 Scale A	30 – 40 Scale A
Polymerized Density	ASTM D-792	1.14 – 1.15 g/cm ³	1.14 – 1.15 g/cm ³

System Availability	Layer Thickness Capability	Support Structure	Available Color
Objet260/350/500 Connex1/2/3™	High Speed mode: 30 microns (0.0012 in.)	SUP705 (WaterJet removable) SUP706B (soluble + WaterJet removable)	<input type="checkbox"/> Translucent
Stratasys J735™/ Stratasys J750™	High Speed mode: 27 microns (0.0011 in.)	SUP705 (WaterJet removable) SUP706B (soluble + WaterJet removable)	<input checked="" type="checkbox"/> Black <input type="checkbox"/> Translucent <input type="checkbox"/> White
J4100™	High Speed mode: 27 microns (0.001 in.)	SUP705 (WaterJet removable)	<input checked="" type="checkbox"/> Black <input type="checkbox"/> Translucent
J826™ Prime / J835™ Prime / J850™ Prime / J850 Pro	High Quality mode: 14 microns (0.00055 in.) High Mix mode: 27 microns (0.001 in.) High Speed mode: 27 microns (0.0011 in.) Super High Speed mode ¹ : 55 microns (0.002 in.)	SUP705 (WaterJet removable) SUP706B (soluble + WaterJet removable)	<input checked="" type="checkbox"/> Black <input type="checkbox"/> Translucent <input type="checkbox"/> White

1 - Not available on the J826 Prime.

Creantz3D Pte Ltd

Singapore

180 Paya Lebar Road
#08-07, Yi Guang Factory Building,
Singapore 409032

Phone: +65 6631 8555
Email: info@creantz3d.com
Website: www.creantz3d.com.sg

stratasys.com

ISO 9001:2015 Certified

Creantz3D Viet Nam Co Ltd

Ho Chi Minh City

Ground floor, HB Tower, No. 669 Dien Bien Phu Street,
Ward 25, Binh Thanh District,
Ho Chi Minh City, Viet Nam

Phone: +8428 6283 8244
Email: vn.info@creantz3d.com
Website: www.creantz3d.com.vn

Ha Noi City

Ground Floor, No. 27/115 Nui True Street,
Kim Ma Ward, Ba Dinh District,
Ha Noi, Viet Nam

Phone: +8424 6273 0936

