

# DraftWhite (MED837)

The DraftWhite™ is a rigid white material, targeted for single-material medical applications such as orthopedics and craniomaxillofacial. The material can be combined with other transparent and Vivid colors allowing for a wide range of medical applications. DraftWhite's mechanical and thermal properties are summarized in the table below.

Property	Standard / Procedure	Value
Tensile Strength	D-638-03	40 – 55 MPa (5,800 – 8,000 psi)
Elongation at Break	D-638-05	5 – 20%
Modulus of Elasticity	D-638-04	2,200 – 3,000 MPa (320,000 – 435,000 psi)
Flexural Strength	D-790-03	70 – 85 MPa (10,000 – 16,000 psi)
Flexural Modulus	D-790-04	2,000 – 2,500 MPa (290,000 – 365,000 psi)
HDT, °C @ 0.45MPa	D-648-06	45 – 50 °C (113 – 122 °F)
HDT, °C @ 1.82MPa	D-648-07	45 – 50 °C (113 – 122 °F)
Izod Notched Impact	D-256-06	20 – 30 J/m (0.375 – 0.562 ft-lb/inch)
Water Absorption	D-570-98 24hr	1.1 – 1.5%
Tg	DMA E	52 – 54 °C (126 – 129 °F)
Shore Hardness (D)	Scale D	83 – 86 (Scale D)
Polymerized Density	Scale M	1.17 – 1.18 g/cm <sup>3</sup>

  

System Availability	Minimum Layer Thickness Capability	Support Structure	Available Color
J5 MediJet™	18 microns (0.0007 in.)	SUP710™ (Waterjet removable)	□ White

## Creutz3D Pte Ltd

### Singapore

180 Paya Lebar Road  
#08-07, Yi Guang Factory Building,  
Singapore 409032

Phone: +65 6631 8555  
Email: [info@creutz3d.com](mailto:info@creutz3d.com)  
Website: [www.creutz3d.com.sg](http://www.creutz3d.com.sg)

[stratasys.com](http://stratasys.com)

ISO 9001:2015 Certified

## Creutz3D Viet Nam Co Ltd

### Ho Chi Minh City

Ground floor, HB Tower, No. 669 Dien Bien Phu Street,  
Ward 25, Binh Thanh District,  
Ho Chi Minh City, Viet Nam

Phone: +8428 6283 8244  
Email: [vn.info@creutz3d.com](mailto:vn.info@creutz3d.com)  
Website: [www.creutz3d.com.vn](http://www.creutz3d.com.vn)

### Ha Noi City

Ground Floor, No. 27/115 Nui True Street,  
Kim Ma Ward, Ba Dinh District,  
Ha Noi, Viet Nam

Phone: +8424 6273 0936